

Fibraworld

Our fiberglass. Your solution.

MINIMAL MECHANICAL CHARACTERISTICS | EUROPEAN NORMATIVE EN 13706

PROPERTY	UNIT	TEST METHOD	MINIMUM PROPERTIES	
			E23	E17
Full Section Test	GPa	Annex D, EN 13706-2:2002	23	17
Tension Modulus-Axial	GPa	EN ISO 527-4	23	17
Tension Modulus-Transverse	GPa	EN ISO 527-4	7	5
Tension Strength-Axial	MPa	EN ISO 527-4	240	170
Tension Strength-Transverse	MPa	EN ISO 527-4	50	30
Pin-Bearing Strength-Axial	MPa	Annex E, EN 13706-2:2002	150	90
Pin-Bearing Strength-Transverse	MPa	Annex E, EN 13706-2:2002	70	50
Flexural Strength-Axial	MPa	EN ISO 14125	240	170
Flexural Strength-Transverse	MPa	EN ISO 14125	100	70
Interlaminar Shear Strength-Axial	MPa	EN ISO 14130	25	15



FIBRAWORLD d.o.o.
Ul. Sarajevska, bb – 76250, Gradačac – Bosna i Hercegovina
TEL/FAX: +387 35 816 375 – info@fibraworld.ba – www.fibraworld.ba
PDV/VAT: 210223810003